PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6:	$\overline{}$		
B32B 27/00	A1	(11) International Publication Number:	WO 96/09928
	AI	(43) International Publication Date:	4 April 1996 (04.04.96)
(21) International Application Number: PCT/NL((22) International Filing Date: 22 September 1995 (2 (30) Priority Data: 9401566 26 September 1994 (26.09.94 9401885 11 November 1994 (11.11.94 (71) Applicant (for all designated States except US): SAI	22.09.99 4) N 4) N	CN, CZ, DE, DK, EE, ES, FI, C KG, KP, KR, KZ, LK, LR, LT, MW, MX, NO, NZ, PL, PT, RO, TJ, TM, TT, UA, UG, US, UZ, V BE, CH, DE, DK, ES, FR, GB, C PT, SE), OAPI patent (BF, BJ, C ML, MR, NE, SN, TD, TG), ARI SZ, UG).	GB, GE, HU, IS, JP, KE, LU, LV, MD, MG, MN, RU, SD, SE, SG, SI, SK, VN, European patent (AT, GR, IE, IT, LU, MC, NL, F, CG, CI, CM, GA, GN,
ALL B.V. [NL/NL]; Kanaaldijk O.Z. 3, NL-8102 H (NL). (72) Inventor; and (75) Inventor/Applicant (for US only): REINDERS, Journal of Maria [NL/NL]; Oude Warkenseweg 1, N PE Warnsveld (NL).	ohannes	With international search report.	
(74) Agent: SCHUMANN, B., H., J.; Amold & Siedsma, inckplein 1, NL-2517 GK The Hague (NL).	Sweel		

(54) Title: COVER FOIL WITH HEAT-ACTIVATED LAYER

(57) Abstract

The invention provides a light-transmitting cover foil intended to be arranged adheringly to a surface, for instance the surface of a carrier plate, optionally bearing information such as letters, numbers, images or the like, which foil consists of a laminate comprising: a first layer plastically deformable only at a relatively high first temperature, for instance in the range of 120 °C - 200 °C and comprising for instance polycarbonate, PMMA, PVC. ABS, PP, PE, which first layer is provided before, during or after joining together to the other layers with a structure, for instance a texture and/or pattern pressed out of its main surface by exerting pressure and increasing temperature to at least the said first temperature, for instance by applying a heated profile roller, a second layer adhered thereto consisting of a dimensionally stable carrier layer comprising for instance polycarbonate, PMMA, PVC, polyester/PET, ABS; and a third layer adhered thereto which is meltable and thus thermally-activated at a relatively low second temperature, for instance in the range of 50 °C - 90 °C and which consists of a hot-melt layer or glue layer, comprising for instance EVA, EEA, EBA, EMA, GBA or other low-melting plastics including polyolefins and copolymer esters, polyacetate esters, softened PVCs; which said layers are mutually connected by adhesive agents, for instance by making use of coextrusion.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

			Harton d Minadam	MR	Mauritania
AT	Austria	GB	United Kingdom	MW	Malawi
AU	Australia	GB	Georgia	NE	Niger
BB	Barbedos	GN	Guinea	NL.	Netherlands
BΕ	Belgium	GR	Greece	NO	Norway
BF	Burkina Faso	HU	Hungary -		New Zealand
BG	Bulgaria	12	Ireland	NZ	Poland
BJ	Benin	JΤ	Italy	PL	
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KC	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic	SD	Sudan
CG	Congo		of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SI	Slovenia
CI	Côte d'Ivoire	KZ	Kazakhstan	SK	Slovakia
CM	Cameroon	' u	Liechtenstein	SN	Senegal
-	China	LK	Sri Lanka	TD	Chad
CN CN	Czechoslovakia	LU	Luxembourg	TG	Togo
CS		ĹV	Larvia	TJ	Tajikistan
CZ	Czech Republic	MC	Monaco	TI	Trinidad and Tobago
DE	Germany	MD	Republic of Moldova	UA	Ukraine
DK	Denmark	MG	Madagascar	US	United States of America
ES	Spein	ML	Mali	UZ	Uzbekistan
FI	Finland	MN	Mongolia	VN	Viet Nam
FR	France	MIN	1.00000.00		
~ .	Cohon :				

COVER FOIL WITH HEAT-ACTIVATED LAYER

The invention relates to a light-transmitting, for instance transparent, cover foil intended for adhesion to an optionally information-carrying surface.

Such a cover foil is known. This known foil 5 comprises a first layer of polyester and a pressure-sensitive or heat-activated glue layer connected thereto.

It is an object of the invention to embody a cover foil such that it can offer a combination of two aspects, that is, a first layer provided with a structure and a heat-activated glue layer. The existing structure may not be adversely affected when the glue layer is activated.

The described, known foil does not meet these requirements.

It is therefore an object of the invention to provide a light-transmitting cover foil which has a structure, for instance a texture and/or a pattern pressed out of its main surface, while provisions are also present to adhere the foil to a surface for covering using simple means and without adversely affecting the existing structure.

In respect of the above the invention provides a light-transmitting cover foil intended to be arranged adheringly to a surface, for instance the surface of a carrier plate, optionally bearing information such as letters, numbers, images or the like, which foil consists of a laminate comprising of:

a first layer plastically deformable only at a relatively high first temperature, for instance in the 30 range of 120°C - 200°C and comprising for instance polycarbonate, PMMA, PVC, ABS, PP, PE, which first layer is provided before, during or after joining together to the other layers with a structure, for instance a texture and/or a pattern pressed out of its main surface by

exerting pressure and increasing temperature to at least the said first temperature, for instance by applying a heated profile roller;

a second layer adhered thereto consisting of a 5 dimensionally stable carrier layer comprising for instance polycarbonate, PMMA, PVC, polyester/PET, ABS; and

a third layer adhered thereto which is meltable and thus heat-activated at a relatively low second temperature, for instance in the range of 50°C - 90°C and 10 which consists of a hot-melt layer or glue layer, comprising for instance EVA, EEA, EBA, EMA, GBA or other low-melting plastics including polyolefins and copolymer esters, polyacetate esters, softened PVCs;

which said layers are mutually connected by 15 adhesive agents, for instance by making use of co-extrusion.

Attention is drawn to the fact that polyester/PET is excluded as material for the first layer.

The invention is based on the insight that the structuring of the first layer can take place in advance and that due to the relatively high softening temperature of the applied material, in the order of for instance 180°C, when the glue layer is activated, for instance at a temperature of 70°C, the first layer including its said structure is not affected, while the glue layer is nevertheless fully activated so that the cover foil can be adhered effectively to the surface for covering.

The second layer consisting for example of 30 polyester is to a large degree non-stretch and non-shrink. This layer also makes possible heating of a strip of cover foil in a laminating machine without this resulting in a softening of the total cover foil such as to limit the ease of handling thereof.

A specific embodiment has the special feature that the first layer and the second layer consist of one integral, chemically substantially homogeneous layer.

Attention is once again drawn to the fact that polyester

SUBSTITUTE SHEET (RULE 26)

is excluded as material for the first layer. In this case both integrated layers must therefore consist of a material from which polyester/PET is excluded.

A specific embodiment has the special feature 5 that the adhesive agents comprise an adhesion-enhancing activation of at least the adhesive surface, for instance a corona treatment, particularly in the case of polyester and polypropylene. Other related treatments such as an ion bombardment may also be appropriate.

The adhesion between the diverse layers can in principle take place in any suitable manner. A specific embodiment is that in which the adhesive agents comprise an adhesive layer such as a layer of primer adhering to both the surfaces for adhesion.

15 All suitable means can be considered to provide the first layer with a structure. A specific embodiment is that in which the first layer is provided in advance with a structure by a mechanical, chemical and/or physical treatment or with a covering layer forming a 20 structure, for instance by vapour-deposition, sputtering or the like.

In general the softening temperature of the first and third layer will have to differ substantially, for instance in the order of at least 30°C. It is in any 25 case necessary to avoid the structure of the fist layer being adversely affected when the cover foil is heat to stick it onto a surface for covering.

In order to ensure a good UV-stability the laminate can comprise a UV-blocking layer, for instance a 30 lacquer layer, present at a suitable position.

CLAIMS

 Light-transmitting cover foil intended to be arranged adheringly to a surface, for instance the surface of a carrier plate, optionally bearing information such as letters, numbers, images or the like, which foil
 consists of a laminate comprising of:

a first layer plastically deformable only at a relatively high first temperature, for instance in the range of 120°C - 200°C and comprising for instance polycarbonate, PMMA, PVC, ABS, PP, PE, which first layer is provided before, during or after joining together to the other layers with a structure, for instance a texture and/or pattern pressed out of its main surface by exerting pressure and increasing temperature to at least the said first temperature, for instance by applying a heated profile roller;

a second layer adhered thereto consisting of a dimensionally stable carrier layer comprising for instance polycarbonate, PMMA, PVC, polyester/PET, ABS; and

a third layer adhered thereto which is meltable 20 and thus heat-activated at a relatively low second temperature, for instance in the range of 50°C - 90°C and which consists of a hot-melt layer or glue layer, comprising for instance EVA, EEA, EBA, EMA, GBA or other low-melting plastics including polyolefins and copolymer 25 esters, polyacetate esters, softened PVCs;

which said layers are mutually connected by adhesive agents, for instance by making use of co-extrusion.

- Cover foil as claimed in claim 1, wherein
 the first layer and the second layer consist of one integral, chemically substantially homogeneous layer.
 - 3. Cover foil as claimed in claim 1, wherein the adhesive agents comprise an adhesion-enhancing activation of at least the adhesive surface, for instance

SUBSTITUTE SHEET (RULE 26)

a corona treatment, particularly in the case of polyester and polypropylene.

- 4. Cover foil as claimed in claim 1, wherein the adhesive agents comprise an adhesive layer such as a 5 layer of primer adhering to both the surfaces for adhesion.
- 5. Cover foil as claimed in claim 1, wherein the first layer is provided in advance with a structure by a mechanical, chemical and/or physical treatment or 10 with a covering layer forming a structure, for instance by vapour-deposition, sputtering or the like.
 - 6. Cover foil as claimed in claim 1, wherein the laminate comprises a UV-blocking layer, for instance a lacquer layer.

INTERNATIONAL SEARCH REPORT

PCT/NL 95/00318

A CLASSI IPC 6	FICATION OF SUBJECT MATTER B32B27/00		
	· · · · · · · · · · · · · · · · · · ·		
	o International Patent Classification (IPC) or to both national class SEARCHED	fication and IPC	
	ocumentation searched (classification system followed by classification	tion symbols)	
IPC 6	B32B	•	
Documentat	ion searched other than minimum documentation to the extent that	such documents are included in the fields a	catch eq
Electronic d	ata base consulted during the international search (name of data base	se and, where practical, search terms used)	
	•		
	IENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the n	elevant passages	Relevant to claim No.
A	US,A,4 063 641 (KUEHN,MITTMAN) 20	O December	1
	see column 6, line 7 - column 6,	line 33	
A	EP,A,O 425 820 (KURARAY CO. LTD.) 1991) 8 May	1
A	FR,A,2 450 853 (ASAHI KASEI KOGYO KABUSHIKI KAISHA) 3 October 1980		1
A	EP,A,O 374 632 (WOLFF WALSRODE AC	G) 27 June	1
	1990	e, canc	_
A	EP,A,O 358 445 (TONEN SEKIYUKAGAI March 1990	KU) 14	1
A	EP,A,O 207 440 (KURARAY CO. LTD.) January 1987) 7	1
Furd	her documents are listed in the continuation of box C.	Patent family members are listed in	n annex.
* Special car	tegories of cited documents :	T later document published after the inte	
	ent defining the general state of the art which is not ered to be of particular relevance	or priority date and not in conflict wi cited to understand the principle or th invention	
	document but published on or after the international	"X" document of particular relevance; the	
"L" docume	ent which may throw doubts on priority claim(s) or is cited to establish the publication date of another	cannot be considered novel or cannot involve an inventive step when the do	cument is taken alone
autia	n or other special reason (as specified) ent referring to an oral disclosure, use, exhibition or	"Y" document of particular relevance; the cannot be considered to involve an in document is combined with one or m	ventive step when the
other r		ments, such combination being obvior in the art.	
		'&' document member of the same patent	family
Date of the	actual completion of the international search	Date of mailing of the international se-	arch report
2:	2 November 1995	28.11.95	
Name and n	nailing address of the ISA Furnment Ratest Office, P.R. SRIS Patentiann?	Authorized officer	
	European Patent Office, P.B. 3818 Patentiaan 2 NL - 2280 HV Rigwijk Td. (+ 31-70) 340-2040, Tz. 31 651 epo nl, Fax: (+ 31-70) 340-3016	Roberts, P	•

INTERNATIONAL SEARCH REPORT

information on patent family members

Application No PCT/NL 95/00318

US-A-4063641 20-12-77 NONE EP-A-0425820 08-05-91 AU-B- 630743 AU-B- 6365590 DE-D- 69015773 DE-T- 69015773 JP-A- 3192140 US-A- 5082743 FR-A-2450853 03-10-80 JP-A- 55118943 JP-C- 1395906 JP-A- 55128458 JP-B- 62005064 JP-C- 1428159 JP-A- 55137964 JP-B- 62035909	05-11-92 11-04-91 16-02-95 11-05-95 22-08-91 21-01-92
AU-B- 6365590 DE-D- 69015773 DE-T- 69015773 JP-A- 3192140 US-A- 5082743 FR-A-2450853 03-10-80 JP-A- 55118943 JP-C- 1395906 JP-A- 55128458 JP-B- 62005064 JP-C- 1428159 JP-A- 55137964 JP-B- 62035909	11-04-91 16-02-95 11-05-95 22-08-91 21-01-92
AU-B- 6365590 DE-D- 69015773 DE-T- 69015773 JP-A- 3192140 US-A- 5082743 	16-02-95 11-05-95 22-08-91 21-01-92
DE-T- 69015773 JP-A- 3192140 US-A- 5082743 FR-A-2450853 03-10-80 JP-A- 55118943 JP-C- 1395906 JP-A- 55128458 JP-B- 62005064 JP-C- 1428159 JP-A- 55137964 JP-B- 62035909	11-05-95 22-08-91 21-01-92
JP-A- 3192140 US-A- 5082743 FR-A-2450853 03-10-80 JP-A- 55118943 JP-C- 1395906 JP-A- 55128458 JP-B- 62005064 JP-C- 1428159 JP-A- 55137964 JP-B- 62035909	22-08-91 21-01-92 12-09-80 24-08-87 04-10-80 03-02-87 25-02-88 28-10-80
US-A- 5082743 FR-A-2450853 03-10-80 JP-A- 55118943	12-09-80 24-08-87 04-10-80 03-02-87 25-02-88 28-10-80
FR-A-2450853 03-10-80 JP-A- 55118943 JP-C- 1395906 JP-A- 55128458 JP-B- 62005064 JP-C- 1428159 JP-A- 55137964 JP-B- 62035909	12-09-80 24-08-87 04-10-80 03-02-87 25-02-88 28-10-80
JP-C- 1395906 JP-A- 55128458 JP-B- 62005064 JP-C- 1428159 JP-A- 55137964 JP-B- 62035909	24-08-87 04-10-80 03-02-87 25-02-88 28-10-80
JP-C- 1395906 JP-A- 55128458 JP-B- 62005064 JP-C- 1428159 JP-A- 55137964 JP-B- 62035909	04-10-80 03-02-87 25-02-88 28-10-80
JP-B- 62005064 JP-C- 1428159 JP-A- 55137964 JP-B- 62035909	03-02-87 25-02-88 28-10-80
JP-C- 1428159 JP-A- 55137964 JP-B- 62035909	25-02-88 28-10-80
JP-A- 55137964 JP-B- 62035909	28-10-80
JP-B- 62035909	
V. V. 1	04-08-87
10 A 197000C	
JP-C- 1372006	07-04-87
JP-A- 56005761	21-01-81
JP-B- 61041307	13-09-86
JP-C- 1492885	20-04-89
JP-A- 56008257	28-01-81
JP-B- 63032622	30-06-88
BE-A- 882117	01-07-80
CA-A- 1157990	29-11-83
DE-A- 3008749	11-09-80
GB-A,B 2048903	17-12-80
NL-A,C 8001397	10-09-80
US-A- 4410595	18-10-83
EP-A-0374632 27-06-90 DE-A- 3842948	28-06-90
CA-A- 2005968	21-06-90
JP-A- 2225043	07-09-90
NO-B- 174769	28-03-94
US-A- 5126198	30-06-92
EP-A-0358445 14-03-90 JP-A- 2070433	09-03-90
US-A- 5075152	24-12-91
EP-A-0207440 07-01-87 JP-C- 1768257	11-06-93
JP-B- 4058382	17-09-92

Form PCT/ISA/210 (petent family ennex) (July 1992)

INTERNATIONAL SEARCH REPORT

information on patent family members

Inti nel Application No PCT/NL 95/00318

Patent document Publication cited in search report date		Patent family member(s)		Publication date	
EP-A-0207440		JP-A-	62011644	20-01-87	
		AU-B-	5890386	08-01-87	
		CA-A-	1240251	09-08-88	
		US-A-	4713296	15-12-87	

Form PCT/ISA/210 (patent family annex) (July 1992)